

## 26 GA - Siliconized Polyester Color Selection

LIGHT STONE **ASH GRAY SADDLE TAN POLAR WHITE** STANDARD SR.60 SRI 71 SR.50 SRI 57 SR .47 SRI 55 SR .48 SRI 55 CHARCOAL GRAY **BURNISHED SLATE** RUSTIC RED **IVY GREEN** SR.28 SRI 27 SR .36 SRI 38 SR.28 SRI 27 SR .27 SRI 26 **IVORY** HAWAIIAN BLUE **DESERT SAND GALVALUME** SR .32 SRI 32 SR .42 SRI 47 SR .65 SRI 78 **COCOA BROWN CRIMSON RED EVERGREEN BERRY** SR.28 SRI 27 SR .33 SRI 34 SR .34 SRI 35 SR .30 SRI 27 **GALLERY BLUE** FERN GREEN BLACK **OLD TOWN GRAY** SR .30 SRI 30 SR .42 SRI 47 SR.27 SRI 26 SR .27 SRI 26 **COLONY GREEN** SR.31 SRI 32

2812 Tallevast Road Sarasota, Florida 34243

**Phone:** 941-755-7073 **Fax:** 941-755-3067 www.tridentbuildingsystems.com

- Solar Reflectivity (SR): Solar reflectivity or reflectance is the measure of a material's ability to reflect solar energy or sunlight from its surface. SR values are numbered 0 to 1.0. A value of 0 indicates that the surface absorbs all solar energy and a value of 1.0 indicates total reflectance. **ENERGY STAR requires an SR value** of 0.25 or higher for steep slope roofing (above 2:12) and an SR value of 0.65 or higher for low slope roofing (2:12 or less). For more information, please visit www.energystar.gov.
- Solar Reflectance Index (SRI): The SRI is used to determine compliance with LEED requirements and is calculated according to ASTM E 1980 using values for reflectance and emissivity. To meet LEED requirements, a roofing material must have an SRI of 29 or greater for steep slope roofing and an SRI value of 78 or higher for low slope roofing. For more information, visit www.usqbc.org.

All colors have a minimum quantity of 5,000 lbs.

Selection of Premium Colors will require additional lead time and cost.





